



Description

Living Proof Silk Low Sheen is the only finish for walls that has a subdued, smooth elegant sheen which makes it suitable for every room. Living Proof Silk Low Sheen resists dirt, stains and scuffing, and to make surfaces easy to clean. Living Proof Acrylic Silk is extremely low in odour, both during and after the application process, allowing rooms to be put back into use immediately after painting.

Uses

Interior walls for medium traffic areas. Walls of bedrooms, dining and family rooms, kitchens, bathrooms and all areas where an attractive, washable finish is required. Particularly suitable for medium traffic areas, including corridors and foyers of office type environments. Not recommended for use in two coat systems on new work.

Recommended for

Highest serviceability and stain resistance.

Features

Advanced Flow Modifiers

Ease of application, good flow, minimal roller splatter

Contains Teflon Micropowder

Superior serviceability, washability, stain and burnish resistance.

Low Odour

Ideal for repainting air conditioned buildings

Special Resin System

Low flame spread compliance suitable for commercial use

Technical

Colour Range

Extensive colour range. Refer to Taubmans Consumer or Architectural/Specifier Colour Systems.

Drying And Recoating

Normally dries in 30 minutes and may be recoated after 2 hours (at 25°C and 50% relative humidity). Note - Drying time may be lengthened in damp, cold or humid conditions.

Gloss Level

Low Gloss (10%) as per AS2311

Odour

Ensure adequate ventilation during use.

Specifications met

APAS 0260/3, AS3730.3

Washability

Excellent

Early Fire Hazard Properties - AS1530.3

Ignitability Index 0 Spread of Flame Index 0 Heat Evolved Index 0 Smoke Developed Index 2

Surface Preparation

New/Bare Work

Seal bare wallboards with Taubmans 3 in 1.

Repaint

Remove all loose and flaking paint. Wash to remove dirt, grease, wallpaper paste and kalsomine. Seal kalsomine residue, undercoat aged enamel and seal stripped wallpaper areas with PrepRight Traditional Undercoat to assist adhesion. Fill holes and cracks with a suitable filler, sand smooth and seal with Taubmans 3 in 1. If mould is present, treat surface with bleach.

Application

Not recommended for use in two coat systems on new work. Do not use abrasive cleaners on the paint finish or expose it to excessive steam in the first 48 hours. Remove dirt and grime with a soft cloth, warm water and mild liquid detergent. Pat dry with a soft cloth.

Application

Apply two liberal coats with a quality brush, roller or spray. A 10mm regular nap roller cover is recommended. Spread paint evenly but do not overspread.

Cleanup

Water

Coverage

Up to 16m²/litre. Coverage will be lower on rough or absorbent surfaces.

Recoat

Recoat after 2 hours at 25°C and 50% relative humidity.

Stirring

Stir Paint with a 25mm wide flat stirrer in a circular lifting motion for at least 5 minutes before use.

Temperature

Do not use at temperatures below 10°C, above 35°C or when humidity is above 85%.
