


Description

Living Proof Silk Gloss is the breakthrough in technology that combines the serviceability and resistance properties of oil based enamels with the low odour and convenience of water based finishes.

Uses

Doors and trim in all areas.

Recommended for

Highest serviceability and stain resistance


Technical
Colour Range

Extensive colour range

Gloss Level

Gloss (75%) as per AS2311

Stain Resistance

Excellent for both water and grease based stains

Drying And Recoating

Dries in 30 minutes, recoat after 2 hours. Note: In cold or humid conditions, drying time is lengthened.

Early Fire Hazard Properties - AS1530.3

Ignitability index 0 Spread of flame index 0 Heat evolved index 0 Smoke developed index 1

Odour

Low

VOC

< 75g/L. LivingProof Silk Gloss is low in Volatile Organic Compounds (VOCs) and is low odour. Meets GBC requirements for interior gloss.


Surface Preparation

Surfaces to be painted must be clean and dry.

New/Bare Work

Seal bare timber and paper faced plasterboard with Taubmans 3in1.

Repaint

Remove loose and flaking paint. Spot undercoat bare timber areas with Taubmans 3in1. Apply a full coat of Taubmans 3in1 to provide adhesion to aged enamel.


Application
Application

Apply to liberal coats with a quality brush or roller. A 10mm or shorter nap roller cover is recommended. Spread evenly but do not overspread. Provide adequate ventilation during use.

Cleanup

Water

Coverage

Up to 16sqm/litre. Coverage will be lower on rough or absorbent surfaces.

Recoat

Recoat after 2 hours at 25C and 50% relative humidity.

Stirring

Stir paint for at least 5 minutes before application.

Temperature

Do not use when temperature is below 10C, or above 35C.
