



Description

Taubmans Endure Doors & Trim is engineered with Nanoguard and has been specifically formulated for busy and high traffic surfaces within the home such as doors, skirting boards, architraves and window frames. Taubmans Endure Doors & Trim with Nanoguard provides superior protection against stains, repeated dusting and washing and wiping, and also protects against mould and mildew growth. Taubmans Endure with Nanoguard has an interlocking molecular structure which creates a protective shield, meaning stains can be wiped away without compromising the quality of the paint.

Uses

Interior and sheltered exterior trim.

Recommended for

Highest performance

 **Features**

Taubmans Endure has a unique interlocking molecular structure that creates a protective shield so that dirt and stains can simply be wiped away without compromising the quality of the paint.

Fungicide Protection

Resists growth of mould and mildew.

Interlocking molecular structure

Protects against stains and regular washing.

Nanoguard

Engineered to Endure, with a 15 year warranty.

 **Technical**

Colour Range

Extensive Colour Range

Gloss Level

Gloss (80%) as per AS2311

Stain Resistance

Excellent for both water and grease based stains

Drying And Recoating

Touch dry in 30 minutes. Recoat in 2 hours at 25C. Allow 4 hours in cooler or humid conditions.

Odour

Low

VOC

Low VOC <75g/L meeting the GBC requirements.

Specifications met

AS3730.12

 **Surface Preparation**

Surfaces must be clean, dry and free from all surface contamination

New/Bare Work

Plasterboard/Masonry and Timber - Undercoat with Taubmans 3in1.

Primed surfaces

Preprimed doors - undercoat with one coat of Taubmans 3in1.

Repaint

Scrape and sand down surface to remove all loose and flaking paint. Sand Glossy or enamel surfaces thoroughly with fine paper (280 mesh or higher) or undercoat with Taubmans 3in1. Prime bare areas with Taubmans 3in1.

 **Application**

Application

Apply 2 coats using a 5mm roller or good quality brush. Ensure that the first coat is completely dry before applying the second coat. Thin coats of paint are better. Avoid overloading the brush or roller.

Cleanup

Water

Coverage

Up to 16sqm/litre. Coverage will be lower on rough or absorbent surfaces.

Recoat

Recoat after 2 hours at 25C. Allow 4 hours in cooler or humid conditions.

Stirring

Stir paint well in a circular lifting motion with a broad flat paddle for 5 minutes before use.

Temperature

Do not use when temperature is below 10C or above 35C.