


Description

A 100% acrylic high performance finish for all interior walls. The unique formula is low in VOC for maximum indoor air quality. Pure Performance Interior contains Microban, which inhibits the growth of harmful bacteria, mould mildew and fungus enabling a cleaner safer built environment.

Uses

Interior walls in commercial and residential high traffic areas requiring a highly washable paint finish. Low odour and low VOC make Pure Performance ideal for new construction and repaint.

Recommended for

Interior walls in high traffic areas.


Features
Antibacterial Protection

Microban® is an exclusive antibacterial technology that protects against growth of bacteria. Microban® technology lasts the life of the paint and will not wear out or wash off.

High Opacity

Excellent coverage and hiding power

Low VOC

<5g/L, suitable for Green Building Council Projects, low odour.

Moisture Resistance

Suitable for wet areas

Mould resistant

Microban® resists the growth of mould and mildew that according to the National Asthma Council Australia may trigger asthma symptoms, hay fever and other allergies.

Special Thickeners

Low roller spatter and ease of application

Washable

Tough, Washable surface


Technical
Specifications met

APAS 0260/2

VOC

<5g/litre. Meets GBC requirements

Gloss Level

20-25%

Colour Range

Wide colour range

Spread Rate

Up to 16sqm/litre. Coverage will be lower on rough or absorbent surfaces.

Drying And Recoating

Touch dry in 30 minutes. Recoat in 2 hours at 25°C. Allow 4 hours in cooler or humid conditions.

Surface Preparation

Surfaces must be clean, dry and free from all surface contamination. Wash down the surface with detergent, followed by a rinse with clean water. Treat mould with bleach then rinse with fresh water. Fill in surface defects such as cracks or holes with a suitable filler, putty or sealant. Avoid using masking tape on wall and ceiling paints.

New/Bare Work

Plasterboard, Masonry & Timber – Undercoat with Pure Performance Prepcoat.

Repaint

Scrape and sand down surface to remove all loose and flaking paint. Spot bare areas with Pure Performance Prepcoat. Sand glossy or enamel surfaces thoroughly with 240 grit paper and undercoat with Pure Performance Prepcoat as required. Ensure an even surface when painting over patchy or contrasting colours by applying one coat of Pure Performance Prepcoat.

Application

Stir paint well in a circular lifting motion for 5 minutes before use with a broad flat paddle. Apply two coats by using a good quality 12mm roller sleeve and brush. Extra coats may be required for application by brush only. It is also important to avoid using poor quality or worn rollers and brushes as they can adversely affect the final finish. Spray Application. Airless Spray or HVLP. Thin up to 10%.

Cleanup

Water, away from drains.

Temperature

Do not paint when temperature is below 10°C, or above 35°C.
